

LFP Series 1441

100μ Soft-PVC monomeric, white matt

Technical Product Information

Grade Characteristics				
Description	Self-adhesive monome	ric soft-PVC, white matt, 2	100 microns	
Application Digital print vinyl for eco-		-solvent, solvent and HP latexbased inksystems		
Certificates B1 flame retardant accord REACH conform		ording to DIN 4102, part 1 pard "Forex Classic"		
Recommended application temperature		min. + 10°C		
Product application temperature		- 30 to + 80°C		
Durability		4 years *		
Shelf life at 23°C / 50% moisture		2 years in original boxes *		
Dimensionstability (FINAT 14)		** adhered to steel , no shrinkage in cross direction (CD)		
		in machine direction (MD) max. 0,2 mm		
Physical Properties Facestock		Value	Unit	Norm
Caliper		100 ± 5	μm	ISO 534
Stretch at break MD		> 160	%	DIN EN ISO 527
Tear resistance MD		> 26	Мра	DIN EN ISO 527
Physical Properties Adhesive		Value	Unit	Norm
Adhesion* R2 \rightarrow Removable, clear		6 ±3	N/25mm	Finat 1
Adhesion* R3xg \rightarrow Removable, grey		10 ±4	N/25mm	Finat 1
Adhesion* P3 \rightarrow Permanent, clear		14 ±6	N/25mm	Finat 1
Adhesion* P3xg → Permanent, grey		16 ±6	N/25mm	Finat 1
Adhesion* P4 \rightarrow Super-Permanent, clear		18 ±6	N/25mm	Finat 1
*Average value				24h on Glass
Physical Properties Liner			Caliper EN ISO 20 534	Substance ISO 536
H14 siliconised Kraftliner			0,144mm	135g/m²
D18 siliconised Kraftliner, double-sided PE-coated			0,150mm	140g/m²
D17 siliconised Kraftliner, double-sided PE-coated, microstructured			0,186mm	165g/m²

Guarantee

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

* Normal storage and handling conditions. Middle-European climate conditions, unprinted. ** depending on the used inks and the interaction between inks and the laminate , the vinyl might shrink, when the printed area are cut. AMC AG Divison Intercoat Telefon: +49-(0)4191-8005-0 Boschstr. 12 Telefax: +49-(0)4191-2450 D-24568 Kaltenkirchen Internet: www.Intercoat.de